

# LUPOY ER5151RFA

Injection Molding , PC/ABS+M/F

## Description

Halogen Free Flame Retardent, High strength  
EPEAT

## Application

IT&OA (Notebook PC housing)

Properties	Test Condition	Test Method	Unit	Typical Value
<b>Physical</b>				
Specific Gravity		ASTM D792	-	1.27
Molding Shrinkage (Flow), 3.2mm		ASTM D955	%	0.2 ~ 0.4
Melt Flow Rate	250 °C/2.16 kg	ASTM D1238	g/10min	9
<b>Mechanical</b>				
Tensile Strength, 3.2mm		ASTM D638		
@ Yield	50mm/min		kg/cm <sup>2</sup>	670
Tensile Elongation, 3.2mm		ASTM D638		
@ Break	50mm/min		%	20
Flexural Strength, 3.2mm	10mm/min	ASTM D790	kg/cm <sup>2</sup>	1,100
Flexural Modulus, 3.2mm	10mm/min	ASTM D790	kg/cm <sup>2</sup>	45,000
IZOD Impact Strength, 3.2mm (Notched)	23 °C -30 °C	ASTM D256	kg·cm/cm kg·cm/cm	7
Rockwell Hardness	R-Scale	ASTM D785	-	
<b>Thermal</b>				
Heat Deflection Temperature, 6.4mm (Unannealed)	18.6kg 4.6kg	ASTM D648	°C °C	92
Vicat Softening Temperature	5kg, 50 °C/h	ASTM D1525	°C	
Ball Pressure Temperature		IEC 60695-10-2	°C	
Burning Rate, 3.2mm		FMVSS 302	mm	
Flammability		UL94		
0.7mm			class	
1.2mm			class	V0
1.5mm			class	
3.0mm			class	V0
Relative Temperature Index		UL 746B		
Electrical			°C	60
Mechanical with Impact			°C	60
Mechanical without Impact			°C	60

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection moulded specimens and after 48 hours storage at 23 °C, 50% relative humidity.

Updated : Jul-09, 2014

# LUPOY ER5151RFA

Injection Molding , PC/ABS+M/F

## Description

Halogen Free Flame Retardent, High strength  
EPEAT

## Application

IT&OA (Notebook PC housing)

## Electrical

Comparative Tracking Index(CTI)	Solution A	IEC 60112	Volts
Surface Resistivity		IEC 60093	Ohm
Volume Resistivity	23℃	ASTM D257	Ohm·m
Arc Resistance	23℃	ASTM D495	Ohm·cm
Dielectric Strength, 1mm	23℃	ASTM D149	kV/mm
Dielectric Constant (10 <sup>6</sup> Hz)	23℃	ASTM D150	sec

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection moulded specimens and after 48 hours storage at 23℃, 50% relative humidity.

## Processing Guide (Injection Molding)

Processing Parameters		Unit	Value
Drying Temperature		℃	75 ~ 85
Drying Time		hrs	3 ~ 4
Maximum Moisture Content		%	0.02
Melt Temperature		℃	245 ~ 275
Cylinder Temperature	Rear	℃	230 ~ 250
	Middle	℃	245 ~ 265
	Front	℃	260 ~ 275
Nozzle Temperature		℃	260 ~ 275
Mold Temperature		℃	60 ~ 80
Back Pressure		kg/cm <sup>2</sup>	
Screw Speed		rpm	40 ~ 70

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.